



Influence of nonlocality on fluorescence from a dipolar emitter coupled to a metallic nanoshell

Tserkezis, Christos; Wubs, Martijn; Mortensen, N. Asger; Stefanou, N.

Publication date:
2015

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Tserkezis, C., Wubs, M., Mortensen, N. A., & Stefanou, N. (2015). *Influence of nonlocality on fluorescence from a dipolar emitter coupled to a metallic nanoshell*. Poster session presented at XXXI Panhellenic conference on Solid State Physics & Materials Science, Thessaloniki, Greece.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Influence of nonlocality on fluorescence from a dipolar emitter coupled to a metallic nanoshell

C. Tserkezis¹, M. Wubs^{2,3}, N. A. Mortensen^{2,3} and N. Stefanou⁴

¹Donostia International Physics Center and Centro de Física de Materiales CSIC-UPV/EHU, Paseo Manuel de Lardizabal 4, Donostia-San Sebastián, 20018, Spain

²Department of Photonics Engineering, Technical University of Denmark, DK-2800 Kgs. Lyngby, Denmark

³Center for Nanostructured Graphene (CNG), Technical University of Denmark, DK-2800 Kgs. Lyngby, Denmark

⁴Department of Solid State Physics, National and Kapodistrian University of Athens, University Campus, 15784 Athens, Greece

E-mail: christos_tserkezis001@ehu.es

It has long been known that emission from classical or quantum emitters depends not only on their intrinsic properties but also on their environment [1]. Experiments on fluorescent molecules or quantum dots in the vicinity of planar metallic surfaces [2] or photonic crystal cavities [3] have shown that, under certain conditions, large enhancement of fluorescence and spontaneous emission rates can be achieved. A particularly promising template for engineering the emitter environment is provided by metallic nanoparticles (NPs). The optical response of these NPs is dominated by localized surface plasmon (LSP) modes, which modify drastically the local density of electromagnetic (EM) states and focus EM fields in regions below the diffraction limit, opening new possibilities to control light-matter interactions.

In the past both fluorescence enhancement and quenching were observed experimentally for emitters close to plasmonic NPs. It is now understood that the final result depends on the interplay between emitter excitation, which is enhanced due to the plasmonic environment, and emission into two decay channels: radiation in the environment and ohmic losses in the metal [4]. An optimum emitter-NP distance, for which the two mechanisms lead to a maximum fluorescence enhancement, can then be obtained. This is shown Fig. 1(a) for an emitter, described here as a classical dipole of dipole moment \mathbf{p} parallel to the external electric field \mathbf{E} , placed at a distance d from the surface of a spherical gold NP with radius $R = 40$ nm. The dipole is excited at wavelength $\lambda = 532$ nm and emits at $\lambda = 560$ nm, values which are appropriate for Rhodamine 6G, and R is selected so that the plasmon resonance lies close to these wavelengths (516 nm). It can be seen that fluorescence, η , is enhanced by about 2.5 times if the dipole is 20 nm away from the NP surface. This value could be significantly enhanced if absorptive losses in the metal were reduced, by choosing for example a different NP material. Silver is a good plasmonic material characterized by low absorptive losses. However, for a silver sphere of similar size, the main LSP peak is at much shorter wavelengths (about 360 nm). In order to bring the LSP resonance within the wavelength region of interest, we take advantage of the tunability provided by hybridization of the plasmonic modes excited at the inner and outer surfaces of a metallic nanoshell [5]. To this end, in Fig. 1(b) we consider a complex NP consisting of a SiO₂ core of radius $R_1 = 32.7$ nm, covered by a silver shell of thickness 7.3 nm,

parameters which were chosen so that the total radius R and LSP wavelength remain the same as in Fig. 1(a). Reduction of ohmic losses in the metallic material leads then to much stronger fluorescence enhancement, of more than an order of magnitude, and this holds for a much larger range of emitter-NP distances [6].




Figure 6: (a) Dependence of fluorescence enhancement, η , for an emitter with dipole moment \mathbf{p} , polarized parallel to the external electric field \mathbf{E} , on distance d from a gold nanosphere of radius $R = 40$ nm. (b) Same as (a), for a silver nanoshell consisting of a SiO_2 core of radius $R_1 = 32.7$ nm and a silver shell of thickness 7.3 nm, so that the total NP radius is $R = 40$ nm.

An important issue that arises when such emitters are placed close to plasmonic NPs, or when the metallic shell of the NP is very thin, is that the nonlocal character of the dielectric function of the metal becomes relevant. For example, it was recently shown, through theoretical studies with a simple hydrodynamic model, that emission rates for a classical dipole in the vicinity of a metallic NP can be significantly reduced because of nonlocality [7]. Within the same model, it has also been shown that strong shifts of the plasmonic modes are also expected [8]. Here we will explore these issues in a systematic way, and study the effect of nonlocality for different NP sizes, shell thicknesses, and emitter distances, by use of both the hydrodynamic model and the recently proposed Generalized Nonlocal Optical Response theory [9]. Our results are expected to shed light on the importance of a description of the optical response of plasmon-emitter hybrids that goes beyond classical electrodynamics and facilitate the design of novel architectures for controlling light-matter interactions.

References

- [1] E. M. Purcell, Phys. Rev. 69 (1946) 681.
- [2] R. R. Chance, A. Prock and R. Silbey, Adv. Chem. Phys. 37 (1978) 1-65.
- [3] P. Lodahl, A. F. van Driel, I. S. Nikolaev, A. Irman, K. Overgaag, D. Vanmaekelbergh and W. L. Vos, Nature 430 (2004) 654-657.
- [4] P. Anger, P. Bharadwaj and L. Novotny, Phys. Rev. Lett. 96, (2006) 113002.
- [5] E. Prodan, C. Radloff, N. J. Halas and P. Nordlander, Science 302 (2003) 419-422.
- [6] C. Tserkezis, *Light emission and propagation in nanostructured plasmonic metamaterials*, PhD Thesis, National and Kapodistrian University of Athens (2012).
- [7] R. Filter, C. Bösel, G. Toscano, F. Lederer and C. Rockstuhl, Opt. Lett. 39 (2014) 6118-6121.
- [8] C. Tserkezis, G. Gantounis and N. Stefanou, J. Phys.: Condens. Matter 20 (2008) 075232.
- [9] N.A. Mortensen, S. Raza, M. Wubs, T. Søndergaard and S. I. Bozhevolnyi, Nature Commun. 5 (2014) 3809.